

5









6

TYPE B/100/3.5

7



10

		A
		В
		С
NOTES		
 <u>GENERAL</u> WHERE APPLICABLE EACH PIN TO BE SUPPLIED WITH A GALVANISED NUT AND GALVANISED WASHER AS SHOWN <u>PINS</u> (a) MATERIAL: PINS TO BE FORGED FROM HOT ROLLED CARBON STEEL GRADE 'AS 1442/CS1030 OR EQUIVALENT (MIN. U.T.S. 470 MPa) (b) PIN SHANK: SHANK LENGTH SHOWN IS SUITABLE FOR STANDARD TIMBER CROSSARMS AND POLE TOP BRACKETS (c) THREAD: THE FORM OF THREAD SHALL BE ISO METRIC COARSE PITCH SERIES 8g TO 'AS1275'. THE THREAD RUNOUT TO BE AS SPECIFIED. (d) HEAD OF INSULATORS PINS: THE MATERIAL OF HEADS TO BE LEAD ALLOY (95% LEAD AND 5% ANTIMONY). IF PLASTICS OR OTHER TYPE OF MATERIAL IS USED FOR HEAD, SUCH MATERIAL SHALL NOT IMPAIR THE MECHANICAL AND ELECTRICAL REDEORMANCE OF THE INCLUATION AND DIM ACCOMPLY 		D
AND ELE THE SHA 'AS 4899 TRUNCAT THAT TH DIAMETEN IS AN IN HEADS T A FIRM C (e) PROTECT QUALITY REQUIREN (f) MINIMUM ESTABLIS BE NOTE	PE OF HEADS AND THREAD FORMS TO BE IN ACCORDANCE WITH '' PARTICULAR ATTENTION SHOULD BE MADE TO THE 'ED THREAD FORM AT THE MAJOR DIAMETER. THIS IS TO ENSURE IE THREAD DOES NOT BIND AGAINST THE THREAD OF THE MINOR R OF THE INSULATOR DURING ASSEMBLY. THE HEAD COLLAR WHICH TEGRAL PART OF PATTERN 'A' AND 'B' HEADS TO BE AS SHOWN. O BE FIRMLY FIXED TO PIN. LEAD HEADS SHOULD BE FITTED WITH 'ARDBOARD CYLINDER FOR PROTECTION DURING TRANSIT. 'IVE COATING: PINS TO BE HOT DIP GALVANISED. THE MASS AND OF COATING AND THE FINISH OF THREADS TO MEET THE MENTS OF 'AS 1214' FALLING LOAD: THE MINIMUM FALLING LOAD SHALL BE SHED BY TYPE TEST IN ACCORDANCE WITH 'AS 4899'. IT SHOULD D THAT THIS FALLING LOAD IS A LOAD APPLIED 25.5 mm ABOVE	E
THE TOP PATTERN PIN AND TOP OF SUCH LO 3. <u>NUTS:</u> NUTS SUPPI TO 'AS 1112 COATING AN 1214' 4. <u>WASHERS:</u> WASHERS S WASHERS T	FOR PATTERNS 'A' AND 'C' PINS AND AT THE PIN TOP FOR I 'B' PINS. FALLING LOADS AND CONSEQUENT WORKING LOADS OF INSULATOR ASSEMBLIES DEPEND ON THE DISTANCE BETWEEN THE THE PIN HEAD AND THE SIDE GROOVE OF THE INSULATOR AND ADS SHOULD BE MODIFIED ACCORDINGLY. LIED SHALL BE HEXAGON DOUBLE CHAMFERED STRENGTH GRADE 5 '. NUTS TO BE HOT DIP GALVANISED. THE MASS AND QUALITY OF ID THE THREAD TOLERANCES TO MEET THE REQUIREMENTS OF 'AS UPPLIED SHALL BE LARGE SERIES TO 'AS 1237' TABLE 3. O BE HOT DIP GALVANISED. THE MASS AND QUALITY OF	F
TO MEET TH 5. <u>SWAN NECK I</u> (a) <u>GENERAL</u> (b) <u>THREAD</u>	E REQUIREMENTS OF 'AS 1214' <u>PINS:</u> SWAN NECK PINS TO COMPLY WITH NOTES 2(a), 2(d), 2(e) AND 2(f). _THE FORM OF COACH SCREW THREAD TO BE IN ACCORDANCE WITH 'AS1393'	G
1:2 R. Mc. D ON ORIGINAL 5-11-1973	OVERHEAD CONSTRUCTION 11kV AND L.V. OVERHEAD MAINS PIN TYPE INSULATOR PIN DETAILS	H
	DRAWING NO 49216 SHEET 1 AMD 4 SIZE A1	

11

12

 \odot

12